

TEK016 GLOSS WHITE

1. Introduction

A range of acrylic based finishes designed to be used in conjunction with most other primers. This range also contains clear coats intended for use over top coat finishes, to enhance final finish, and to improve environmental and physical protection.

2. Where to use

All types of metallic and rigid plastics surfaces when used in conjunction with the appropriate primers.

3. Where not to use

Surfaces treated with primers of unknown composition, without first ascertaining suitability of use

4. Benefits

- Enhanced covering power
- Excellent durability
- Fast drying high gloss finish
- Excellent resistance to sunlight and colour fade
- Enhanced adhesion to primed surfaces

5. Physical properties [Acrylic finish bases except where stated].

| | |
|--------------------------------------|--|
| Appearance | Black, white and clear liquids with characteristic paint solvent odours. |
| pH | Not applicable |
| Specific Gravity | 0.94 – 1.09 |
| Viscosity | Up to 1,500cPs |
| Non Volatiles % m/m | 25 - 55 |
| Active Content % m/m, as supplied | 7.5 – 15.0 |
| Flammability, as supplied | Extremely Flammable, flash point below -20°C |
| Composition Data, as supplied | A solvent based solution of an acrylic resin containing a range of pigments, extenders, plasticizers, thixotropes and ultra violet light absorbers dispersed in a butane/propane/isobutane based propellant. |
| Volatile Organic Content as supplied | Compliant with EU Directive 2004/42/CE |
| Service Temperatures | Up to 80°C |
| Application Temperatures | 15 - 25°C |



6. Application Details

Prepare the primed area to be treated, ensuring freedom from dust, grime, greases, oils etc, with TEK038 Universal Degreaser or suitable alternative and allow to dry. If necessary, the surface may be flattened by abrading the surface lightly, using 1200 grade wet and dry abrasive paper, and solvent treated as described above to remove any dust. Shake the can thoroughly for at least two minutes. Repeat shaking at regular intervals during use. Apply sparingly from a distance of 20 – 25cm. Apply typically 2 to 3 light coats as necessary to achieve total and even coverage, leaving 10 - 15 minutes between each application. Allow to fully harden for at least 24 hours after application of final acrylic finish coating and application of the clear lacquer. On completion of use, invert can and depress actuator for a few seconds to prevent nozzle blockage.

7. Availability

500ml aerosol



Manufactured by JBL European leaders in the manufacture of aerosols and consumer chemicals. JBL has been manufacturing specialist chemicals for more than 180 years, trusted innovators since 1830.

