

## TEK009 FAST DRY SPOT PRIMER GREY

### 1. Introduction

A fast drying primer designed for use on small repairs.

### 2. Where to use

Suitable for use on most metals and rigid plastics.

### 3. Where not to use

Surfaces previously treated with alkyd paints, without first ascertaining suitability.

### 4. Benefits

- Ideal for spot and SMART repairs
- Minimal sanding
- Excellent adhesion to polyester body fillers, metals and rigid plastics
- Fast Drying
- Compatible with virtually all types of automotive paint

### 5. Physical properties [Primer except where stated].

Appearance	Coloured liquid with characteristic paint solvent odours.
pH	Not applicable
Specific Gravity	1.155 – 1.225
Viscosity	500 – 1,500cPs
Non Volatiles % m/m	50 – 60
Active Content % m/m, as supplied	15 – 25
Flammability, as supplied	Extremely Flammable, flash point below -20°C
Composition Data, as supplied	A solvent based solution of an acrylic resin containing a range of pigments, extenders and thixotropes dispersed in a butane/propane/isobutane based propellant.
Volatile Organic Content as supplied	Compliant with EU Directive 2004/42/CE
Service Temperatures	Up to 80°C
Application Temperatures	15 - 25°C



### 6. Application Details

Prepare the area to be treated, ensuring freedom from dust, grime, traffic film, greases, oils etc, using TEK038 Universal Degreaser or suitable alternative and allow to dry. Rust, other surface contamination, and loosely adhering matter should be removed using an appropriate grade of wet and dry abrasive paper. Following preparation the surfaces should be further treated with TEK038 Universal Degreaser and allowed to dry. If in doubt about the composition of the substrate, undertake a small test application on an inconspicuous area prior to use to ensure suitability. Shake the can thoroughly for at least two minutes. Repeat shaking at regular intervals during use. Apply sparingly from a distance of 20 – 25cm. Apply 2 to 3 coats as necessary to achieve total and even coverage, leaving at least 15 minutes between each application. Allow at least 24 hours between application of final coating and preparation for any subsequent finishes that may be required. On completion of use, invert can and depress actuator for a few seconds to prevent nozzle blockage.

### 7. Availability

500ml aerosol