

## TEK029 BRAKE CALIPER RED

### 1. Introduction

These products are designed primarily for the customisation of brake calliper and brake drums.

### 2. Where to use

Designed for use primarily on brake calipers and drums.

### 3. Where not to use

This product is designed for the use specified, and should be used only for the intended application

### 4. Benefits

- High Gloss Finish
- Extremely Durable
- High Gloss Finish
- Extremely Durable
- Excellent resistance to sunlight and colour fade

### 5. Physical properties [Caliper paint bases except where stated].

Appearance	Coloured liquids with characteristic paint odours
pH	Not applicable
Specific Gravity	0.9 – 0.955
Viscosity	Low viscosity pourable liquids
Non Volatiles % m/m	30 - 40
Active Content % m/m, as supplied	10 - 15
Flammability, as supplied	Extremely Flammable, flash point below -20°C
Composition Data, as supplied	Solvent based solutions of alkyd and acrylic resins containing pigments, plasticisers and wetting agents dispersed in a butane/propane/isobutane based propellant.
Volatile Organic Content as supplied	Compliant with EU Directive 2004/42/CE
Service Temperatures	Up to 100°C
Application Temperatures	15 - 25°C



### 6. Application Details

Protect all non metallic components including seals, hoses etc, and prepare the area to be painted, if necessary, ensuring freedom from dust, grime, greases, oils etc with TEK038 Universal Degreaser or suitable alternative and allow to dry. Do not apply when the callipers or drums are hot, or in damp or humid weather. Shake the can thoroughly for at least two minutes. Repeat shaking at regular intervals during use. Apply sparingly from a distance of 15 – 25cm. Apply 2 to 3 light coats as necessary to achieve total and even coverage, leave 15 to 30 minutes between each application. Allow to dry for 24 hours before handling. On completion of use, invert the can and depress the actuator for a few seconds to prevent nozzle blockage. Note: This product must not be applied to rubber components, brake discs, pads or shoes. Should contact occur, remove immediately or replace as necessary. After 12 hours this product cannot be re-coated for 6 weeks.

### 7. Availability

500ml aerosol